



# Geotube

## GT750

GT750 is a black coloured fabric composed of high tenacity polypropylene yarns, which are woven into a stable network such that the yarns retain their relative position. GT750 is used to manufacture Geobag, Geotube® and Geocontainer® systems for engineering applications. GT750 is inert to biological degradation and resistant to naturally encountered chemicals, alkalis, and acids.

Mechanical Properties	Test Method	Unit	Characteristic Value	
			MD	CD
Wide Width Tensile Strength	ISO 10319	kN/m	120	120
Wide Width Tensile Elongation	ISO 10319	%	20	15
Factory Seam Strength	ISO 10321	kN/m	60	80
CBR Puncture Strength	ISO 12236	kN	14	
Drop Cone	ISO 13433	mm	10	
			<b>Average Value</b>	
Characteristic Opening Size	ISO 12956	mm	0.25	
Water Flow Rate	ISO 11058	l/m <sup>2</sup> /s	15	
Abrasion Resistance	ASTM D 4886	% strength retained	75	
UV Resistance (at 500 hours)	ASTM D 4355	% strength retained	90	

**Disclaimer:** TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.